

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
31 March 2005 (31.03.2005)

PCT

(10) International Publication Number  
WO 2005/028747 A1

(51) International Patent Classification<sup>7</sup>: D21F 1/66  
(21) International Application Number:  
PCT/FI2004/000549

(22) International Filing Date:  
20 September 2004 (20.09.2004)

(25) Filing Language: Finnish

(26) Publication Language: English

(30) Priority Data:  
20031376 24 September 2003 (24.09.2003) FI

(71) Applicant (for all designated States except US): METSO  
PAPER, INC. [FI/FI]: Fabianinkatu 9 A. FI-00130  
HELSINKI (FI).

(72) Inventors; and

(75) Inventors/Applicants (for US only): HIETANJEMI,  
Matti [FI/FI]: Kanjoninreuna 8 A 2. FI-33720 TAMPERE  
(FI). KOKKONEN, Kari [FI/FI]: Pikkukönkä 6. FI-40520  
JYVÄSKYLÄ (FI).

(74) Agent: FORSSÉN & SALOMAA OY: Berikinkatu 2.  
FI-00100 HELSINKI (FI).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, GR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MY, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.


(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,  
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance  
Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR MAKING A LAYERED PAPER OR BOARD WEB



(57) Abstract: A method for manufacturing a layered paper or board web, in which method thick stock (M) delivered to the paper machine is diluted with tail water and the diluted stock (M<sub>1</sub>) is fractionated in order to produce two different stock fractions (A, B). The first stock fraction (A), which contains on an average finer material than the second stock fraction (B), is conducted into the surface layer or layers of the paper or board web, and the second stock fraction (B), which contains on an average coarser material than the first stock fraction (A), is conducted into the middle layer or layers of the paper or board web. Before feeding into a headbox (15), the coarse stock fraction (B) from fractionation is diluted with water whose consistency is substantially lower than the consistency of the water added into the thick stock (M) before fractionating. When water, which contains less solids from the stock than the normal tail water, is used to dilute the coarse stock fraction, the stock fractions used for different layers of the paper or board web can, better than before, maintain their different properties, which improves the result of layering in paper or board manufacturing.

1A2370511-11 32 MAR 2006

## Method for Making a Layered Paper or Board Web

5 The invention relates to a method for making a layered paper or board web, in which method thick stock delivered to a paper machine is diluted with tail water and the diluted stock is fractionated to produce two different stock fractions of which, the first stock fraction, containing on an average finer material than the second stock fraction, is conducted into the surface layer or layers of the paper or board web, and  
10 the second stock fraction, containing on an average coarser material than the first stock fraction, is conducted into the middle layer or layers of the paper or board web.

A stock feed system for a multi-layer headbox is disclosed in the US patent No. 5,746,889, in which different stock concepts are produced out of the same fresh stock  
15 to be fed into different layers of the multi-layer headbox. The stock feed system contains at least one screen for transferring long fibers out of the stock that is destined to form the surface layer of the paper into the stock that is destined to form a layer placed in the interior of the paper. The system may also contain another screen for transferring short fibers out of the stock that is destined to form the layer placed in the  
20 interior of the paper into the stock that is destined to form the surface layer of the paper.

Fractionating methods that apply centrifugal cleaning are disclosed in WO published applications Nos. 0 129 311 A1 and 0 222 947 A1, in which accept from the first  
25 centrifugal cleaning step is transferred into the surface layers of the web to be formed, and the accept from a second or lower step is transferred into the middle layers of the web to be formed. By fractionating the stock, lower fines contents and higher average fiber length can be achieved in the middle layers of the web than in the surface layers of the web. On the other hand, higher fines and filler contents can be achieved in the

surface layers of the web than in the middle layers, which, among other things, improves the printing properties of the paper.

5 The accept fibers separated during the fractionating of the stock are on an average shorter, thinner and more pliable, and the accept contains more fines and filler than the reject. For simplicity's sake, the accept from fractionation will be referred to as the fine stock fraction and the reject from fractionation will be referred to as the coarse stock fraction.

10 It is typical for fractionating that the consistency of the accept is decreased and the consistency of the reject is increased compared to the consistency of the feed. Because of this, the reject often has to be diluted before it can be conducted into the headbox of the paper machine. In WO 0 222 947, the rejects from the fractionating stages are diluted with tail water taken from a wire pit before they are transferred into  
15 the next stage. In WO 0 129 311, the same tail water is being used for diluting both the accept and the reject before they are fed into the different layers of the multi-layer headbox. When the coarse stock fraction intended for the middle layers of the web is diluted with "impure" tail water, i.e. containing plenty of fines and filler, at least some of the advantages obtained with fractionating are lost. Because of the tail water,  
20 the drainability of the reject can go down almost to the level of the accept and the filler content can go up to near the filler content of the accept.

The object of the invention is to provide an improved method for manufacturing a web from a stock by layering the different fractions thereof. Especially, the object is  
25 to maintain the different properties of the stock fractions produced by fractionating, whereupon the objectives set for the layering of the stock are easier to reach.

In order to obtain these and other objects that will become evident later, the method according to the invention is characterized by what is defined in the characterizing

part of claim 1.

When the coarse stock fraction is diluted with water that contains less solids originating from the stock than normal tail water, the different properties of the stock  
5 fractions used for different layers of the paper or board web can be maintained better than before, which improves the result of layering in paper or board manufacturing.

Tail water is a filtrate removed from the web being formed on the wire section, which water is collected into a wire pit or the like and which contains fines and filler  
10 originating from the paper stock. A major part of the solids contained in the primary tail water is returned into the process by using tail water for diluting the thick stock in the short circulation of the paper machine.

Water suitable for diluting the coarse stock fraction is characterized by the fact that  
15 the consistency of the water is substantially lower than the consistency of the tail water used for diluting the thick stock before fractionating. Preferably, the consistency of the diluting water is less than 60 % of the consistency of the primary tail water.

20 Examples of possible water fractions suitable for diluting the reject are cloudy and clear filtrate from the recovery of fibers, water coming from suction flatboxes, separately collected paper machine spray water, water coming from the press section and tail water fractioned by clarification or some other method. One option is to dilute tail water with a substantially cleaner water fraction such that the consistency  
25 of water used for diluting the coarse stock fraction is substantially lower than the original consistency of the tail water.

In the following, the invention will be described with reference to the examples in the appended figures, but the intention is not to limit the invention to these only.

Figure 1 shows a schematic view of manufacturing of layered paper using fractionating of the stock and a multi-layer headbox.

Figure 2 shows manufacture of a multi-layer web using fractionating of the stock and  
5 two different web-forming units.

According to figure 1, thick stock M is delivered into the paper machine via a wire pit 10, where it is diluted with tail water originating from the wire section. The diluted stock M<sub>1</sub> is conducted with a pump P<sub>1</sub> into a first centrifugal cleaning step 11 of a centrifugal cleaner equipment, where the stock is fractionated into two stock fractions A and B. Fractionating is performed so, that the first stock fraction will contain fibers that on an average are thinner, shorter and more pliable and also more fines and filler than the second stock fraction B. Because of this, the stock fractions are in the following referred to as the fine stock fraction A and the coarse stock fraction B.

15

The fine stock fraction A from fractionation is conducted as two component flows A<sub>1</sub> and A<sub>2</sub> through pumps P<sub>A1</sub> and P<sub>A2</sub> and machine screens 13<sub>A1</sub> and 13<sub>A2</sub> into two layers 14<sub>A1</sub> and 14<sub>A2</sub> of a multi-layer headbox 15 that are used to form the top and bottom layers of the manufactured paper or board web.

20

The coarse stock fraction B from fractionation is diluted and the diluted stock flow B<sub>1</sub> is conducted through a pump P<sub>2</sub> into a second centrifugal cleaning step 12 of the centrifugal cleaner equipment, where impurities are extracted from the stock. The accept B<sub>2</sub> from the centrifugal cleaning step 12 is conducted through a pump P<sub>B</sub> and a machine screen 13<sub>B</sub> into a layer 14<sub>B</sub> of the multi-layer headbox that is used for  
25 forming the middle layer of the paper and board web.

As the fractionating increases the consistency of the coarse stock fraction B, the stock B must be diluted before conducting it into the headbox 15. Conventionally, tail

water  $D_1$  taken from the wire pit 10, containing substantial amount of fibers, fines and filler, is used for dilution. In the solution according to the invention, a water flow  $D_0$ , whose consistency is lower than the consistency of the tail water  $D_1$  taken from the wire pit 10, is conducted into diluting the coarse stock fraction B. This water can, for example, be taken from fiber recovery screen, spray water recovery or from suction flatboxes. Also water from the wire pit 10 can be used as dilution water, provided that enough solids have been extracted from it in a separate process stage (not shown). Dilution water, which is substantially cleaner than the tail water, can also be obtained by diluting water from the wire pit with a cleaner water fraction.

10

Figure 2 illustrates another solution according to the invention. There, the diluted stock  $M_1$  is fractioned in the first centrifugal cleaning step 11 of the centrifugal cleaner equipment into two stock fractions A and B. The fine stock fraction A from fractionation is conducted into a headbox 16, which feeds the stock on a fourdrinier wire 18 for forming a first web  $W_1$ . The coarse stock fraction B from fractionation is diluted with a water flow  $D_0$ , whose consistency is lower than that of the tail water  $D_1$  from the wire pit 10, and it is conducted into a second centrifugal cleaning step 12 of the centrifugal cleaner equipment. The cleaned stock  $B_2$  is conducted through a pump  $P_B$  and a machine screen  $13_B$  into a headbox 17, which feeds the stock on a second fourdrinier wire 19 for forming a second web  $W_2$ . The second web  $W_2$  is carried by the wire 19 on top of the first web  $W_1$  on the wire 18 and the webs  $W_1$  and  $W_2$  are joined together to form a two-layered board web.

When manufacturing multi-layer web, there naturally can be more than two separate web forming units and the web forming units may comprise besides a fourdrinier wire also a gap former.

Instead of the above-described centrifugal cleaning device, fractionation can also be carried out in a manner known per se by using pressure screens. By adapting the

fractionating techniques and the reject ratio, different types of properties can be obtained for the different layers of the web. There can naturally be more than one fractionating stage.

- 5 In the following the patent claims will be given, and the details of the invention may show variation within the scope of the inventive idea defined in said claims and differ from the details given above for the sake of example only.

10

15

20

25

## Claims

1. A method for manufacturing a layered paper or board web, in which method thick stock (M) delivered to a paper machine is diluted with tail water and the diluted stock  
5 (M<sub>1</sub>) is fractionated to produce two different stock fractions (A, B), of which the first stock fraction (A), containing on an average finer material than the second stock fraction (B), is conducted into the surface layer or layers of the paper or board web, and the second stock fraction (B), containing on an average coarser material than the first stock fraction (A), is conducted into the middle layer or layers of the paper or  
10 board web, **characterized** in that the coarse stock fraction (B) is, before being fed into a headbox (15; 17), diluted with water having a consistency that is substantially lower than the consistency of the tail water added into thick stock (M) before fractionating.
- 15 2. A method according to claim 1, **characterized** in that the coarse stock fraction (B) from fractionation is diluted with water, whose consistency is at the most 60 % of the consistency of the tail water used for diluting the stock before fractionating.
- 20 3. A method according to any of the preceding claims, **characterized** in that water from fiber recovery, suction flatboxes and/or press section and/or separately collected fabric conditioning water and/or cleaned tail water is/are used for diluting the coarse stock fraction (B) from fractionation.
- 25 4. A method according to any of the preceding claims, **characterized** in that tail water that has been diluted with a water type substantially cleaner than the tail water itself is used for diluting the coarse stock fraction (B) from fractionation.
5. A method according to any of the preceding claims, **characterized** in that the coarse stock fraction (B) from fractionation is conducted into the headbox (15; 17)



through a cleaning device (12) and that the stock fraction (B) in question is diluted before it is fed into said cleaning device (12).

6. A method according to any of the preceding claims, **characterized** in that  
5 fractionating is carried out by centrifugal cleaners (11).

7. A method according to any of the preceding claims, **characterized** in that fractionating is carried out by screens.

10 8. A method according to any of the preceding claims, **characterized** in that fractionating is carried out by in two or more stages.

9. A method according to any of the preceding claims, **characterized** in that the fine stock fraction (A) from fractionation is conducted into at least one layer (14<sub>A1</sub>, 14<sub>A2</sub>)  
15 of the multi-layer headbox (15) used for forming a surface layer of the paper or board web, and the coarse stock fraction (B) from fractionation is conducted into at least one other layer (14<sub>B</sub>) of the same multi-layer headbox (15) used for forming a middle layer of the paper or board web.

20 10. A method according to any one of claims 1 to 8, **characterized** in that the fine stock fraction (A) from fractionation is conducted into at least one headbox (16) used for forming a surface layer of the multi-layer web, and the coarse stock fraction (B) from fractionation is conducted into at least one other headbox (17) used for forming a middle layer of the multi-layer web.

1/2




FIG. 1




FIG. 2

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 2004/000549

## A. CLASSIFICATION OF SUBJECT MATTER

IPC7: D21F 1/66

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7: D21F

Documentation searched other than minimum: documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6210529 B1 (TAISTO HUHTELIN), 3 April 2001 (03.04.2001), claim 1, abstract --	1-10
A	US 6267845 B1 (JOUKO HAUTALA ET AL), 31 July 2001 (31.07.2001), claims 1,2, abstract --	1-10
A	WO 02086233 A1 (METSO PAPER, INC.), 31 October 2002 (31.10.2002), claims 1,2, abstract -- -----	1-10

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

22 December 2004

Date of mailing of the international search report

23-12-2004

Name and mailing address of the ISA/

Swedish Patent Office, ~~Box 5055, S-102 42 STOCKHOLM~~

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Nils Nordin/Els

Telephone No. +46 8 782 25 00

# INTERNATIONAL SEARCH REPORT

Information on patent family members

27/11/2004

International application No.

PCT/FI 2004/000549

US	6210529	B1	03/04/2001	AT	259907	T	15/03/2004
				AU	4620099	A	30/12/1999
				CA	2334706	A	16/12/1999
				DE	19926111	A,C	16/12/1999
				DE	69914919	D	00/00/0000
				EP	1102888	A,B	30/05/2001
				SE	1102888	T3	
				FI	103677	B	00/00/0000
				FI	981328	D	00/00/0000
				JP	2002517636	T	18/06/2002
				WO	9964669	A	16/12/1999
-----							
US	6267845	B1	31/07/2001	AT	272741	T	15/08/2004
				AU	4619999	A	30/12/1999
				BR	9911529	A	20/03/2001
				CA	2334657	A	16/12/1999
				CN	1126839	B	05/11/2003
				CN	1305549	T	25/07/2001
				DE	29909960	U	09/09/1999
				DE	69919175	D	00/00/0000
				EP	1102887	A,B	30/05/2001
				SE	1102887	T3	
				FI	103676	B	00/00/0000
				FI	981327	D	00/00/0000
				JP	3490973	B	26/01/2004
				JP	2002517635	T	18/06/2002
				WO	9964668	A	16/12/1999
-----							
WO	02086233	A1	31/10/2002	EP	1399621	A	24/03/2004
				FI	111391	B	00/00/0000
				FI	20010830	A	24/10/2002
				US	20040144513	A	29/07/2004
-----							